

### **Product Description**

Laminated Gypsum Plasterboard with 4 tapered edges of 12.5 mm thickness and 1,200 mm in width, manufactured using a continuous lamination process, including the formation of its tapered edges.

### **Application**

Construction of interior drywall systems: wall partitions, wall linings and continuous ceilings. Its 4 tapered edges prevent the joints from being visible, providing a high quality finish.

## **Storage and conservation**

Store the boards on flat surfaces and never outdoors, keeping them covered, away from sunlight and rain. Maximum stacking of the boards: 6 pallets.

# **Conditions of installation**

Consult Placo® Installation Manual.



### **Handling**

During the unloading, the aperture of the forks of the forklift should be a minimum of 1/3 of the length of the board being handled, always placing the load in the centre of the forks on the forklift. Special care is advised for handling 3,000mm boards.













Characteristic	Value	
Norms	EN 520,Gypsum plasterboards. Definitions, requirements and test methods	
Board thickness	12.5 mm	
Board Thickness Tolerance	± 0.5 mm	
Board liner color	Ivory	
Board reverse color	Grey	
Long Edge Type	Tapered Edge (TE)	
Short Edge Type	Tapered Edge (TE)	
Thermal conductivity	0.25 W/m.K	
Water vapour diffusion factor $\boldsymbol{\mu}$	10	
Fire Reaction (EN Standard)	A2-s1, d0	
CE board type designation	A	
Approximate weight per m <sup>2</sup>	8.1 kg/m²	
Flexural breaking load longitudinal	> 550 N	
Flexural breaking load transversal	> 210 N	

Length (mm)	Width (mm)	Packaging Boards/Pallet
2000 1	1200 <sup>2</sup>	36
2500 <sup>1</sup>	1200 <sup>2</sup>	36

<sup>10/-5</sup> 

<sup>&</sup>lt;sup>2</sup> Width tolerance (mm): +0/-4



Cotas expresadas en mm.