



PLACO® MONTANTE 55

Metal profiles

Product Description

Galvanised steel metal profile manufactured using cold-rolling. “C” shaped vertical element which fits inside the rails, constituting the framework of the load-bearing structure of gypsum plasterboard partitions or self-supporting cladding. The core has some inverted “U” shaped holes to run systems inside the surface of the wall.

Storage and conservation

Store on flat surfaces and never outdoors, keep covered, away from sunlight and rain.

Conditions of installation

Consult Placo® Plasterboards constructive solutions Manual and Placo® Installation Manual.




Handling

The use of Category 4 cut resistant gloves is recommended.

Characteristic	Value
Norms	EN 14195, Metal framing components for gypsum plasterboard systems - Definitions, requirements and test methods
Fire Reaction (EN Standard)	A1
Type of material	DX51D
Corrosion Protection Coating Class	Z140
Weight per linear meter	0.61 kg
Metal Thickness	0.6 mm
Thickness Tolerance	± 0.05 mm
Moment of inertia	$I_x > 2,57 \text{ cm}^4$

Length (mm)	Tolerance (mm)	Un/Package	Un/Pallet
2790	± 3	10	420
2990	± 3	10	420
3290	± 4	10	420
3590	± 4	10	420
3790	± 4	10	420

Dimensions (mm)	Dimensions (mm)	Tolerance
a	54.50 mm	± 0.5
Ala b	36.00 mm	± 0.5
Ala c	34.00 mm	± 0.5
d	5.00 mm	± 1



This information and, in particular, the recommendations relating to the application and use of the product, are based on the current technical knowledge and experience of SAINT-GOBAIN PLACO IBERICA S.A. of its products, which must be correctly stored, handled and installed within their useful life. The terms of the General Conditions of Sale and Supply of Saint-Gobain Placo S.A. apply to all orders. SAINT-GOBAIN PLACO IBERICA S.A. reserves the right to change the technical specifications of the product without prior notice. It is the user's responsibility to find out and use the latest and updated version of the product data sheets, a copy of which will be sent to those who request it. The content of this document is not exhaustive. Saint-Gobain Placo S.A. accepts no responsibility in the event of the use of our products in a way that does not conform to the instructions supplied by Saint-Gobain Placo S.A. Within the legal limits, Saint-Gobain Placo S.A. will not be responsible for loss of profit or indirect damages.