



PLACO[®] PPM 13 1200

Boards







Product Description

Laminated Gypsum Plasterboard with cardboard on both sides, with a thickness of 12.5 mm and a width of 1,200 mm, conveniently additivated to reduce surface absorption of water (H1 according to EN 520).

Application

Construction of interior drywall systems: wall partitions and self-supporting cladding and continuous ceilings. It will be used mainly in rooms with average humidity such as kitchens and bathrooms.

Storage and conservation

Store the boards on flat surfaces and never outdoors, keeping them covered, away from sunlight and rain. Maximum stacking of the boards: 6 pallets.

Conditions of installation

Consult Placo® Installation Manual.



Handling

During the unloading, the aperture of the forks of the forklift should be a minimum of 1/3 of the length of the board being handled, always placing the load in the centre of the forks on the forklift. Special care is advised for handling 3,000 mm boards.













Characteristic	Value	
Norms	EN 520,Gypsum plasterboards. Definitions, requirements and test methods	
Board thickness	12.5 mm	
Board Thickness Tolerance	± 0.5 mm	
Board liner color	Green	
Board reverse color	Grey	
Long Edge Type	Tapered Edge (TE)	
Short Edge Type	Square Edge (SE)	
Thermal conductivity	0.25 W/m.K	
Water vapour diffusion factor $\boldsymbol{\mu}$	10	
Fire Reaction (EN Standard)	A2-s1, d0	
CE board type designation	H1	
Total water absorption	≤ 5%	
Surface water absorption	< 180 g/m2	
Approximate weight per m²	8.6 kg/m²	
Flexural breaking load longitudinal	≥ 550 N	
Flexural breaking load transversal	≥ 210 N	

Length (mm)	Width (mm)	Packaging Boards/Pallet
2000 1	1200 ²	36
2500 ¹	1200 ²	36
2600 ¹	1200 ²	36
2700 ¹	1200 ²	36
3000 ¹	1200 ²	36

¹ Tolerance of length (mm): +0/-5

² Tolerance of width (mm): +0/-4



Cotas expresadas en mm.