



PLACO[®] PPM 15 1200

Boards







Product Description

Laminated Gypsum Plasterboard with cardboard on both sides, with a thickness of 15 mm and a width of 1200 mm, conveniently additivated to reduce surface absorption of water (H1 according to EN 520).

Application

Construction of interior drywall systems: wall partitions and self-supporting cladding and continuous ceilings. It will be used mainly in rooms with average humidity such as kitchens and bathrooms.

Storage and conservation

Store the boards on flat surfaces and never outdoors, keeping them covered, away from sunlight and rain. Maximum stacking of the boards: 6 pallets.

Conditions of installation

Consult Placo® Installation Manual.



Handling

During the unloading, the aperture of the forks of the forklift should be a minimum of 1/3 of the length of the board being handled, always placing the load in the centre of the forks on the forklift. Special care is advised for handling 3,000 mm boards.













Characteristic

Board thickness

Board liner color

Long Edge Type

Short Edge Type

Thermal conductivity

Water vapour diffusion factor μ

Fire Reaction (EN Standard)

CE board type designation

Total water absorption

Surface water absorption

Approximate weight per m² Flexural breaking load longitudinal

Flexural breaking load transversal

Board reverse color

Board Thickness Tolerance

Norms

Length	Width (mm)	Packaging
(mm)	Width (mm)	Boards/Pallet
2500 1	1200 ²	30
2600 ¹	1200 ²	30
2700 ¹	1200 ²	30
3000 ¹	1200 ²	30

¹ Tolerance of length (mm): +0/-5

² Tolerance of width (mm): +0/-4



Cotas expresadas en mm.

Value

± 0.5 mm

Tapered Edge (TE)

Square Edge (SE)

0.25 W/m.K

A2-s1, d0

< 180 g/m2

10.5 kg/m²

≥ 650 N

≥ 250 N

Green

Grey

10

Н1

≤ 5%

EN 520, Gypsum plasterboards. Definitions, requirements and test methods

